

Test Report No.66.161.15.3963.01R1
Dated:2015-04-21



Applicant: XIAMEN GREENMOUNTAIN IMP. & EXP. CO. LTD
Address: 22/F BUILDING 2 , THAIHOT PLAZA , XIUFENG ROAD , FUZHOU , FUJIAN , CHINA
Contact Person: HAPPY ZENG

Sample Description: PLANTPACK DESICCANT
End Use: MOIST ABSORPTION
Style No.: PB25
Country Of Origin: CHINA

Sample Received Date: 2015-03-23


Date of Testing: 2015-03-24 to 2015-04-20

Sample submitted: The sample(s) was (were) submitted by applicant and identified.

Test result(s): Refer to the Section 3

Remark:

1. This report supersedes the test report 66.161.15.3963.01 issued on 2015-04-20



Remark: The result relates only to the items tested.

No extract, abridgment or abstraction from a test report may be published or used to advertise a product without the written consent of the General Manager of TÜV SÜD Certification and Testing (China) Co., Ltd. Xia Men Branch. The results contained herein apply only to the particular sample tested and to the specific test carried out and not to samples of the current production line.

Laboratory:
TÜV SÜD Certification and Testing
(China) Co., Ltd.,
Xiamen Branch
Form No.: TC_XMN_F_04.05E
Rev: A/0

Phone: +86 592 7706188
Fax: +86 592 7706288
E-mail:
report.softlines@tuv-sud.cn
www.tuv-sud.cn

Regd. Office:
TÜV SÜD Certification and Testing (China) Co., Ltd., Xiamen
Branch
Unit 401 No.93 Huli Industrial Park, Meixi Road, Tong'an
District, Xiamen 361100 P. R. China





1. Description of the test subject:

	
1. Desiccant	





2. Conclusion:

	Testing items	Conclusion
1.	Moisture Absorption Test	#

Note: Pass= Meet Requirement
#= No Comment
N/A = Not Applicable

Fail= Below Requirement
- = Did Not Perform
* = See Remark





3 Test Results

3.1 Moisture Absorption Test: In house method


Test atmosphere:25°Cx90 %RHx15Days

	Test Sample 001A	Test Sample 001B	Test Sample 001C
Culture Dish weighed (g)	36.5519	33.9108	34.6518

Date	Weight (g)					
	Test Sample 001A		Test Sample 001B		Test Sample 001C	
	Total weight	Net weight	Total weight	Net weight	Total weight	Net weight
2015.04.03 10 : 30	37.5539	1.0020	34.9459	1.0351	35.6836	1.0318
2015.04.04 10 : 30	37.8905	1.3386	35.2918	1.3810	36.0307	1.3789
2015.04.05 10 : 30	37.8982	1.3463	35.3045	1.3937	36.0474	1.3956
2015.04.06 10 : 30	37.9051	1.3532	35.3104	1.3996	36.0547	1.4029
2015.04.07 10 : 30	37.9076	1.3557	35.3051	1.3943	36.0470	1.3952
2015.04.08 10 : 30	37.8955	1.3436	35.2932	1.3824	36.0401	1.3883
2015.04.09 10 : 30	37.8935	1.3416	35.2916	1.3808	36.0381	1.3863
2015.04.10 10 : 30	37.8915	1.3396	35.2908	1.3800	36.0336	1.3818
2015.04.11 10 : 30	37.8889	1.3370	35.2896	1.3788	36.0303	1.3785
2015.04.12 10 : 30	37.8869	1.3350	35.2879	1.3771	36.0298	1.3780
2015.04.13 10 : 30	37.8853	1.3334	35.2818	1.3710	36.0274	1.3756
2015.04.14 10 : 30	37.8926	1.3407	35.2892	1.3784	36.0333	1.3815
2015.04.15 10 : 30	37.8964	1.3445	35.2918	1.3810	36.0367	1.3849
2015.04.16 10 : 30	37.9010	1.3491	35.2958	1.3850	36.0385	1.3867
2015.04.17 10 : 30	37.9079	1.3560	35.2997	1.3889	36.0412	1.3894
2015.04.18 10 : 30	37.9120	1.3601	35.3080	1.3972	36.0486	1.3968




4 Testing curves





4 Testing curves



TÜV SÜD Certification and Testing (China) Co., Ltd. Xia Men Branch

Prepared by:

Reviewed by:



Temple Deng
Softlines Department

Jamie Zhang
Softlines Department

-- END OF THE TEST REPORT --